

Auditing Test Report

Test Report No.:SA13-4043-34

Date: 03/02/2022

Client

Saudi Vitrified Clay Pipe Co.

P.O. Box 6415

Riyadh 11442

Kingdom of Saudi Arabia

Sampling Date: 30/01/2022

Test Date: 31/01/2022

Auditing Purpose:

Testing of Vitrified Clay Pipes jointed by system C according to EN 295-1:2013

Size Description:

Nominal Size: DN 500 * 2500 mm

Jointing System: System C

Class: 160

Description of Sampling

Samples were collected randomly from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro

Underlying specification /description of the tests

EN 295-1:2013	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
GSO EN 295-1:2008	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
EN 295-2:2013	"Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"
EN 295-3:2012	"Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods"



Test Results of DN 500 ES 2.5m

Test Report No.:SA13-4043-34

	Test Type		Unit	Sample 1	Sample 2	Sample 3	Req.	Result
	Pipes	Marking (visual Inspection)		-	✓	✓	✓	✓
Crushing Strength		KN/m	94	88	95	≥ 80	✓	
Internal Barrel Diameter "D1"		mm	502	500	501	≥ 487	✓	
Length		mm	2502	2501	2500	2500 ^{+4%} _{-1%}	✓	
Water Tightness		L/m ²	0.02	0.02	0.03	≤ 0.04	✓	
Deviation from Straightness		mm	0.6	0.5	0.4	< 3.0	✓	
Squariness of Ends		Socket	mm	5.5	6.1	7.2	< 10.0	✓
		Spigot	mm	5.8	6.8	6.5		
Airtightness		mm	21	22	23	Drops ≤ 25	✓	
Water Absorption		%	4.9	4.9	4.8	≤ 6 %	✓	
Joint Assembly	Joint Interchangeability		mm	637.2	636.9	637.1	637 ± 0.5	✓
	Watertightness under Angular Deflection		-	No leak, Deflection applied is 30 mm/m for 5 min.			No visible leakage	✓
	Watertightness under Shear		-	No leak, Shear force applied is 12.5 KN for 15 min.			No visible leakage	✓
	Continuity of Invert		mm	4.1	4.2	3.9	≤ 5.0	✓

(Signature)

FUGRO - SUHAIMI LTD

Neesar Ahmed

